

Technical Information

TRACTOTHAN®



TRACTOTHAN®

TRACTOTHAN® is a VULKOLLAN®* composite material developed by us with the same properties as VULKOLLAN®. Special TPU granules incorporated into the tread ensure increased wheel grip, thus improving starting properties, preventing slip and improving braking effects. TRACTOTHAN® is therefore particularly suitable for in-plant transportation and use on wet and soiled surfaces.

- Increased braking effect
- Reduced risk of sliding
- High load capacities
- High speeds

Technical Information	Standard			Unit	Value
Hardness	DIN	ISO	7619-1	Shore A	93 (± 3)
Density	DIN EN	ISO	1183-1	g/cm ³	approx. 1,2
Elongation at break	DIN	DIN	53 504	%	approx. 640
Stress value at 100%	DIN	DIN	53 504	MPa	9,0 - 9,5
Rebound resilience	ISO	DIN	53 512	%	55 - 60
Determination of tear strength	ISO	DIN	34-1	kN/m	60 - 65
Compression set 70 h, 23°C	ISO		815-1	%	10 - 11
Abrasion resistance			4649	mm ³	40
Coefficient of friction (traction) on wet floor at 8000 N				--	0,15
Rolling resistance at 20°C of charge (average)				%	0,9 - 1,0
Starting resistance at 20°C of charge (average)				%	1,2 - 1,5

All values indicated in this table are approximative values resulting from our own tests or information given by our raw material suppliers. The standardised tests refer to special test samples. Therefore these values are not directly applicable to wheels and castors. Furthermore these values change under such influences as temperature, humidity, duration of charge, rate of deformation, etc. For more information please visit www.raedervogel.de.

No legal obligation.

* VULKOLLAN® is a registered trademark of the Covestro Group.