

Technical Information

VULKOLLAN® ELF



VULKOLLAN® ELF

VULKOLLAN®* ELF is a special material based on DESMODUR® 15* for deflecting electrostatic charges. Through the addition of electrically conductive components, the discharge is carried out through the entire tread and over the entire contact area, regardless of the wear on the tread. VULKOLLAN® ELF comfortably exceeds the requirements set by the DIN EN 12527 ff standard for electrical volume resistance and is particularly suitable for use in operations where there is risk of

fire or explosion, in areas with highly densified, charged air or with extremely concentrated dust particles.

- Prevents electrostatic charges
- High load capacities

Technical Information	Standard			Unit	Value
Hardness	DIN	ISO	7619-1	Shore A	95 (± 3)
Density	DIN EN	ISO	1183-1	g/cm ³	approx. 1,2
Elongation at break	DIN	DIN	53 504	%	approx. 570
Stress value at 100%	DIN	DIN	53 504	MPa	7,8 - 8,2
Rebound resilience	ISO	DIN	53 512	%	50 - 55
Determination of tear strength	ISO	DIN	34-1	kN/m	55 - 55
Compression set 70 h, 23°C	ISO		815-1	%	10,5 - 11,5
Abrasion resistance			4649	mm ³	43
Coefficient of friction (traction) on wet floor at 8000 N				--	0,11
Rolling resistance at 20°C of charge (average)				%	0,8 - 0,9
Starting resistance at 20°C of charge (average)				%	1,1 - 1,4

All values indicated in this table are approximative values resulting from our own tests or information given by our raw material suppliers. The standardised tests refer to special test samples. Therefore these values are not directly applicable to wheels and castors. Furthermore these values change under such influences as temperature, humidity, duration of charge, rate of deformation, etc. For more information please visit www.raedervogel.de.

No legal obligation.

* VULKOLLAN® and DESMODUR® are registered trademarks of the Covestro Group.