

# Technical Information

## VULKOLLAN® hydrolysis-stabilized



### VULKOLLAN® hydrolysis-stabilized

VULKOLLAN® hydrolysis-stabilized is a highly elastic, cross-linked polyurethane elastomer based on DESMODUR® 15\*. Like all types of materials made from VULKOLLAN®\* the product features outstanding mechanical properties, with a special additive it protects against hydrolysis. As a result, VULKOLLAN® hydrolysis-stabilized is particularly suited for use in warm and tropical environments, as for example, within the tropics or for applications in electroplating.

- Long service life
- High load capacities
- High speeds
- High impact resilience
- Hydrolysis-stabilized

Technical Information	Standard			Unit	Value
Hardness	DIN	ISO	7619-1	Shore A	93 (± 3)
Density	DIN EN	ISO	1183-1	g/cm <sup>3</sup>	approx. 1,2
Elongation at break	DIN	DIN	53 504	%	approx. 650
Stress value at 100%	DIN	DIN	53 504	MPa	9,5 - 10,0
Rebound resilience	ISO	DIN	53 512	%	55 - 60
Determination of tear strength	ISO	DIN	34-1	kN/m	60 - 65
Compression set 70 h, 23°C	ISO		815-1	%	10 - 11
Abrasion resistance			4649	mm <sup>3</sup>	39
Coefficient of friction (traction) on wet floor at 8000 N				--	0,1
Rolling resistance at 20°C of charge (average)				%	0,8 - 0,9
Starting resistance at 20°C of charge (average)				%	1,1 - 1,4

All values indicated in this table are approximative values resulting from our own tests or information given by our raw material suppliers. The standardised tests refer to special test samples. Therefore these values are not directly applicable to wheels and castors. Furthermore these values change under such influences as temperature, humidity, duration of charge, rate of deformation, etc. For more information please visit [www.raedervogel.de](http://www.raedervogel.de).

No legal obligation.

\* VULKOLLAN® and DESMODUR® are registered trademarks of the Covestro Group.